

33 005

Translucent flexible sheet made of high quality PVC material  
 Large format for backlighting and prints  
 For interior use  
 Made-to-measure in desired shape and size

### ICELAND

WEIGHT PER UNIT AREA	0,400 Kg/m <sup>2</sup> (±10%)	EN 14716
THICKNESS	0,300 mm (±10%)	EN ISO 2286-3
WIDTH OF STRIPS	2,60 m stretched	
TENSILE STRENGTH*	lengthways > 12 Mpa	EN ISO 527-3
	diagonally > 10 Mpa	EN ISO 527-3
ELONGATION AT BREAK*	lengthways > 140 %	EN ISO 527-3
	widthways > 150 %	EN ISO 527-3
REACTION TO FIRE	B-s2,d0	EN 13501-1
LIGHT TRANSMISSION**	46%	ISO 13468-2 Illuminant D65
HAZE***	> 99 %	ISO 14782-1999
MAX. TEMPERATURE OF USE	60°C	
MIN. TEMPERATURE OF USE	> -5°C	
DIMENSIONAL STABILITY	lengthways < 4,5 %	EN 14716
	diagonally < 4,5 %	(10 min. à 70°C)
PRODUCT CERTIFICATION	CE	EN 14716
PERMEABILITY TO WATER VAPOUR	< 50 g/m <sup>2</sup> per 24h	EN 14716
INDOOR AIR EMISSIONS**	A+	
RECYCLABLE	totally	
STORAGE	Indoors, at room temperature, out of direct sunlight	
CLEANING	Cleaning products supplied by EXTENZO®, and microfiber or chamois leather. Use of solvents, methylated spirits, abrasive cleaners or sharp objects is forbidden.	



\* In normal conditions: 23°C (± 1°C), relative humidity of 50%.

\*\* LNE report for a standard D65 illuminant (6500°K), the values for A (2856°K) and C (6774°K) illuminants differ by less than 1%, the weighting for the acuity of the human eye is taken into account. The Haze characterises the degree of blurring.

\*\*\* Defined by decree of 19 April 2011 published in the Official Journal of the French Republic.

No known dermatological and allergic reactions, or sensitivity or irritation. The residual vinyl chloride content is below 1 ppm.

The information we provide concerning this product is based on our current knowledge and as manufacturer we cannot provide any guarantee and accept no liability for factors beyond our control or knowledge.